

Spin-relaxation and magnetoresistance in FM/SC/FM tunnel junctions

S. Takahashi^a, T. Yamashita^a, H. Imamura^b, and S. Maekawa^a

^aInstitute for Materials Research, Tohoku University, Sendai 980-8577, Japan

^bGraduate School of Information Sciences, Tohoku University, Sendai 980-8579, Japan

The effect of spin relaxation on tunnel magnetoresistance (TMR) in a ferromagnet/superconductor/ferromagnet (FM/SC/FM) double tunnel junction is theoretically studied. The spin accumulation in SC is determined by balancing of the spin-injection rate and the spin-relaxation rate. In the superconducting state, the spin-relaxation time τ_s becomes longer with decreasing temperature, resulting in a rapid increase of TMR. The TMR of FM/SC/FM junctions provides a useful probe to extract information about spin-relaxation in superconductors.

Spin-polarized tunneling plays an important role in the spin-dependent transport of magnetic nanostructures [1]. The spin-polarized electrons injected from ferromagnets (FM) into nonmagnetic metals (NM) such as a normal metal, semiconductor, and superconductor creates a nonequilibrium spin polarization in NM [2–8]. The efficient spin injection and weak spin-relaxation during transport are required for practical applications. A number of experiments for observing the spin relaxation time τ_s in SCs has been reported by using a spin-injection device [5] and by the conduction electron spin resonance [9,10].

A double tunnel junction FM/SC/FM containing superconductor (SC) sandwiched between two FMs is a unique system to investigate nonequilibrium phenomena caused by spin injection, especially the magnetoresistive effects by competition between superconductivity and spin accumulation [11–13]. The pronounced magnetoresistance effects is brought about by a long spin relaxation time τ_s in SC, which corresponds to a long spin-diffusion length. In this article, we take into account the coherence effect of superconductivity on the spin-relaxation due to spin-orbit scattering by impurities [15], and demonstrate that the tunnel magnetoresistance (TMR) of the FM/SC/FM junction exhibits a large enhancement due to the increase of τ_s in the superconducting state.

We consider a FM/SC/FM double tunnel junction. The left and right electrodes are made of a ferromagnet, and the central one is a supercon-

ductor with thickness d smaller than the spin-diffusion length λ_S . The magnetizations of FMs are aligned either parallel or antiparallel. Using the Fermi's golden rule, we calculate the spin-dependent tunnel currents across the junctions [11,12]. In the following we consider the case that the bias voltage V is much smaller than the superconducting gap parameter Δ . In this case, the shift of chemical potential $\delta\mu$ for up-spin ($-\delta\mu$ for down-spin) electrons due to spin accumulation is much smaller than Δ , so that the tunnel current I_i^σ across the i th junction ($i = 1, 2$) becomes

$$I_1^\uparrow(V) = G_1^\uparrow \chi(T) [V/2 - \delta\mu/e], \quad (1)$$

$$I_1^\downarrow(V) = G_1^\downarrow \chi(T) [V/2 + \delta\mu/e], \quad (2)$$

$$I_2^\uparrow(V) = G_2^\uparrow \chi(T) [V/2 + \delta\mu/e], \quad (3)$$

$$I_2^\downarrow(V) = G_2^\downarrow \chi(T) [V/2 - \delta\mu/e]. \quad (4)$$

Here, $G_i^\sigma \chi(T)$ ($i = 1, 2$) is the tunnel conductance for electrons with spin σ in the superconducting state, G_i^σ is that in the normal state, and

$$\chi(T) = 2 \int_{\Delta}^{\infty} \frac{E_{\mathbf{k}}}{\sqrt{E_{\mathbf{k}}^2 - \Delta^2}} \left(-\frac{\partial f_0}{\partial E_{\mathbf{k}}} \right) dE_{\mathbf{k}}, \quad (5)$$

where $f_0(E_{\mathbf{k}})$ is the Fermi distribution function and $E_{\mathbf{k}} = \sqrt{\xi_{\mathbf{k}}^2 + \Delta^2}$ the dispersion of quasiparticles, $\xi_{\mathbf{k}}$ being one-electron energy relative to the chemical potential.

The spin density $\mathcal{S}$ accumulated in SC is determined by balancing the spin injection rate $(d\mathcal{S}/dt)_{\text{inj}}$ with the spin relaxation rate $\mathcal{S}/\tau_s$:

$$(I_{1\uparrow} - I_{1\downarrow}) - (I_{2\uparrow} - I_{2\downarrow}) = 2e\mathcal{S}/\tau_s, \quad (6)$$

where τ_s is the spin relaxation time and

$$\mathcal{S} = \frac{1}{2} \sum_{\mathbf{k}} [f_{\uparrow}(E_{\mathbf{k}}) - f_{\downarrow}(E_{\mathbf{k}})] \approx N(0)\chi(T)\delta\mu, \quad (7)$$

where $f_{\sigma}(E_{\mathbf{k}}) \sim f_0(E_{\mathbf{k}}) - (\partial f_0/\partial E_{\mathbf{k}})\sigma\delta\mu$ is the distribution function of quasiparticles with spin σ and $N(0)$ is the normal-state density of states in SC.

It follows from Eqs. (1)-(7) that the tunnel currents for the parallel (P) and antiparallel (AP) alignments are given by

$$I_P = \chi(T)V/R_T, \quad (8)$$

$$I_{AP} = \left[\frac{1 - P^2 + \Gamma_s}{1 + \Gamma_s} \right] \chi(T)V/R_T, \quad (9)$$

where $R_T = 1/G_T$ ($G_T = G_i^{\uparrow} + G_i^{\downarrow}$) is the tunnel resistance and Γ_s is the relaxation parameter

$$\Gamma_s = e^2 N(0) R_T A d / \tau_s, \quad (10)$$

with A being the junction area. Therefore, we have the TMR ratio at low bias ($V \ll \Delta$)

$$TMR = \frac{I_P - I_{AP}}{I_{AP}} = \frac{P^2}{1 - P^2 + \Gamma_s}, \quad (11)$$

where $P = (G_i^{\uparrow} - G_i^{\downarrow})/(G_i^{\uparrow} + G_i^{\downarrow})$ is the tunneling spin polarization. For a weak spin relaxation ($\Gamma_s \ll 1$), $TMR = P^2/(1 - P^2)$, while for a strong spin-relaxation ($\Gamma_s \gg 1$), $TMR = P^2/\Gamma_s \ll 1$.

In SC, the spin relaxation is caused by the spin-orbit scattering from impurities or grain boundaries. The spin-orbit interaction $\mathcal{H}_{so}$ via impurity potential $V_{imp}(\mathbf{r})$ is given by

$$\mathcal{H}_{so} = -i(\hbar/2mc)^2 \vec{\sigma} \cdot [\nabla V_{imp}(\mathbf{r}) \times \nabla], \quad (12)$$

where $\vec{\sigma}$ is the Pauli spin matrix. The scattering matrix elements over quasiparticle states $|\mathbf{k}\sigma\rangle$ has the form:

$$\langle \mathbf{k}'\sigma' | \mathcal{H}_{so} | \mathbf{k}\sigma \rangle = i\lambda_{so} \tilde{V}_{\mathbf{k}'\mathbf{k}} \left[\vec{\sigma}_{\sigma'\sigma} \cdot (\hat{\mathbf{k}} \times \hat{\mathbf{k}}') \right], \quad (13)$$

where λ_{so} is the spin-orbit coupling parameter, $\tilde{V}_{\mathbf{k}'\mathbf{k}} = (u_{\mathbf{k}'}u_{\mathbf{k}} - v_{\mathbf{k}'}v_{\mathbf{k}}) V_{imp}$, $|u_{\mathbf{k}}|^2 = 1 - |v_{\mathbf{k}}|^2 = \frac{1}{2}(1 + \xi_{\mathbf{k}}/E_{\mathbf{k}})$, and $\hat{\mathbf{k}} = \mathbf{k}/|\mathbf{k}|$. Using the golden rule formula, we obtain the spin-relaxation rate due to the spin-flip scattering by $\mathcal{H}_{so}$:

$$\left(\frac{\partial \mathcal{S}}{\partial t} \right)_{sf} = \frac{2\pi}{\hbar} n_i \sum_{\mathbf{k}'\mathbf{k}} |\langle \mathbf{k}' \downarrow | \mathcal{H}_{so} | \mathbf{k} \uparrow \rangle|^2 \delta(E_{\mathbf{k}} - E_{\mathbf{k}'})$$




Figure 1. Temperature dependence of the spin-relaxation time Γ_s^N . Inset shows $\chi(T)$ and $2f_0(\Delta)$ versus T , which are used to calculate τ_s .

$$= -\frac{8\lambda_{so}^2 N(0)}{9\tau_{imp}} \int_{\Delta}^{\infty} [f_{\uparrow}(E_{\mathbf{k}}) - f_{\downarrow}(E_{\mathbf{k}})] dE_{\mathbf{k}}, \quad (14)$$

where $1/\tau_{imp} = (2\pi/\hbar)n_i V_{imp}^2 N(0)$ is the scattering rate by impurities and n_i is the impurity concentration.

From Eqs. (7) and (14), we determine the relaxation time τ_s from $(\partial \mathcal{S}/\partial t)_{sf} = -\mathcal{S}/\tau_s$, and obtain

$$\tau_s = \tau_{sf} \frac{\int_{\Delta}^{\infty} \frac{E}{\sqrt{E^2 - \Delta^2}} [f_{\uparrow}(E) - f_{\downarrow}(E)] dE}{\int_{\Delta}^{\infty} [f_{\uparrow}(E) - f_{\downarrow}(E)] dE}, \quad (15)$$

where $\tau_{sf} = 9\tau_{imp}/8\lambda_{so}^2$ is the spin-flip scattering time in the normal state. Note that the expression of Eq. (15) is valid for $v_F \tau_{sf} \gg \xi_0 = \hbar v_F/\pi \Delta_0$ [14]. For $\delta\mu \ll \Delta$, Eq. (15) reduces to

$$\tau_s = [\chi(T)/2f_0(\Delta)] \tau_{sf}, \quad (16)$$

which is the same as the result of Yafet [15], but differs from the result of Zhao and Hershfield [16]. Equation (15) is a generalization of Yafet to the case of arbitrary value of $\delta\mu$.

The temperature dependence of the spin-relaxation parameter Γ_s is scaled to the normalized spin-relaxation time τ_s/τ_{sf} by the relation $\Gamma_s = (\tau_{sf}/\tau_s) \Gamma_s^N$, where $\Gamma_s^N = e^2 N(0) R_T A d / \tau_{sf}$ is the relaxation parameter in the normal state. Figure 1 shows the temperature dependence of




Figure 2. Tunnel magnetoresistance as a function of temperature for different value of the relaxation parameter. Inset shows the TMR versus Γ_s^N in the normal state.

τ_s/τ_{sf} . Above $T = T_c$, the spin relaxation time τ_s coincides with the spin-flip scattering time τ_{sf} . As temperature T is lowered below T_c , τ_s becomes longer with decreasing T and behaves as $\tau_s \simeq (\pi\Delta/2k_B T)^{1/2}\tau_{sf}$ at low T .

Figure 2 shows the temperature dependence of the normalized TMR for different values of Γ_s^N . The inset shows the TMR versus Γ_s^N in the normal state. In the case of $\Gamma_s^N > 1$, which corresponds to the case that the spin-relaxation rate is larger than the spin-injection rate in the normal state, the TMR above T_c is suppressed compared with the optimal value 33% for $\Gamma_s^N = 0$ and $P = 0.5$ as shown in the inset of Fig. 2. However, in the superconducting state below T_c , the TMR increases rapidly with decreasing T due to the increase of τ_s , and recovers the optimal TMR in the limit of $T \rightarrow 0$. If one uses the values of $R_TA = 100 \Omega\mu m^2$, $\tau_{sf} = 10^{-10}\text{sec}$, $d = 10 \text{ nm}$, and $N(0) = 10^{22}/(\text{eVcm}^3)$, then one obtains $\Gamma_s^N = 10$. Notice that in the case of strong spin-relaxation ($\Gamma_s^N \gg 1$), the TMR becomes proportional to τ_s , so that the temperature dependence

of $TMR/TMR(T_c)$ coincides with that of τ_s/τ_{sf} as shown by the dashed curve in Fig. 2. The result indicates that the TMR of FM/SC/FM junctions provides a method to extract important information about spin-relaxation in superconductors.

The authors are grateful to A. Fert and M. Johnson for fruitful discussions. A part of this work was done during stay (S.T.) in CNRS/Thomson-CSF, France. This work is supported by a Grant-in-Aid for Scientific Research from Ministry of Education. S.M. acknowledges support of the Humboldt Foundation.

REFERENCES

1. *Spin dependent transport in magnetic nanostructures*, edited by S. Maekawa and T. Shinjo (Gordon and Breach Sci. Pub., London) (in press).
2. M. Johnson and R. H. Silsbee, Phys. Rev. Lett. **55** (1985) 1790.
3. T. Varet and A. Fert, Phys. Rev. B **48** (1993) 7099.
4. M. Jemeda *et al.*, Nature **410** (2001) 345.
5. M. Johnson, Appl. Phys. Lett. **65** (1994) 1460.
6. V. A. Vas'ko *et al.* Phys. Rev. Lett. **78** (1997) 1134.
7. Z. W. Dong *et al.* Appl. Phys. Lett. **71** (1997) 1718.
8. T. Daibo *et al.* (unpublished).
9. D.C. Vier and S. Schultz, Phys. Lett. **98** (1983) 283.
10. N. M. Nemes *et al.*, Phys. Rev. B **61** (2000) 7118.
11. S. Takahashi, H. Imamura, and S. Maekawa, Phys. Rev. Lett. **82** (1999) 3911.
12. S. Takahashi *et al.*, J. Appl. Phys. **87** (2000) 5227; *ibid.* **89** (2001) 7505.
13. S. Takahashi, H. Imamura, and S. Maekawa, Physica C **341-348** (2000) 1515.
14. K. Maki, Phys. Rev. B **8** (1973) 191; L. R. Tagirov *et al.*, J. Phys. F **17** (1987) 695.
15. Y. Yafet, Phys. Lett. A **98** (1983) 287.
16. H. L. Zhao and S. Hershfield, Phys. Rev. B **52** (1995) 3632. In their result, $\chi(T)$ is missing in Eq. (16).